298AF Alumin-R

DESCRIPTION:

Karnak #298AF Alumin-R is a PREMIUM grade, single component, SBS rubber modified asphalt reflective coating specially formulated with aluminum pigment to be used as a reflective elastomeric coating over modified bitumen membranes, BUR asphalt roofs, properly sloped residential concrete roofs and metal roof surfaces.

ADVANTAGES:

- 1. Easy to apply.
- 2. 24 hour cure.
- 3. Tough, flexible elastic, rubber-like film.
- 4. Excellent adhesion over clean asphalt surfaces.
- 5. Excellent water and water vapor resistance.
- 6. Excellent weather resistance.
- 7. Good resistance to salts and alkalies.
- 8. Aluminum reflectant characteristics.

USES:

Karnak #298AF Alumin-R is recommended as a coating for use on modified bitumen membranes, BUR, concrete tile, metal and mobile home roofs.

SURFACE PREPARATION:

All surfaces to be coated with Karnak #298AF Alumin-R must be clean, dry, free from oil, grease, and loose debris. New BUR asphalt roofs should be allowed to weather 90-180 days before coating.

Modified bitumen membranes should be coated immediately after the membrane has been laid into place. Metal roofs should be cleaned with a power washer using a minimum of 3000-3500 psi to remove rust and loose flaking prior to the application of Karnak #298AF Alumin-R. New metal should be allowed to weather 30 days before coating.

Karnak #298AF Alumin-R should be **mechanically mixed** for several minutes before application.

Badly weathered or alligatored asphalt surfaces should be primed with Karnak 100AF Non-Fibered Emulsion or 220AF Fibered Emulsion prior to coating with 298AF Alumin-R. Allow emulsion primer to cure a minimum of 3-5 days before application of aluminum coating. Patch and repair all seams, flashings, cracks, leaks and damaged areas with appropriate materials. **APPLICATION:**

Karnak #298AF Alumin-R can be applied by brush, roller or spray. If spray









732-388-0300 • 800-526-4236 • FAX: 732-388-9422 WEB: http://www.karnakcorp.com

298AF Alumin-R

equipment is utilized, use a standard heavy duty spray pump. Equipment manufacturer should be consulted for more complete information.

COVERAGE RATE:

Recommended rate of 1.5 to 2 gallons per 100 sq. ft. in one application.

CLEAN UP:

Tools may be cleaned with mineral spirits or similar solvent.

PHYSICAL PROPERTIES:

Weight per Gallon: 8.5 lbs. 47% Solids by Weight: Color: Silver

0.15 mg.per sq. cm. Permeability:

Cure Time: 24 to 48 hrs. Performance Temp.Range: -40°F to 180°F 300% D-412 Elongation: 300% D-412 Tensile Strength:

CAUTION:

Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

Note: Coating Modified Bitumen Membranes with Aluminum **Coatings:**

Karnak recommends coating torch-applied modified bitumen membranes as soon as possible after the membrane is installed.

Karnak's experience, laboratory and field tests, as well as NRCA, RCMA and ARMA reports, indicate that aluminum coating will reduce the combined effects of ultraviolet rays, heat and moisture, which, especially on APP modified bitumens, enhance exudation that can cause discoloring and delamination of any surface coating.

COLD-PROCESS SYSTEMS AND COATINGS, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE.









298AF Alumin-R

PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) "THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING."

If further information is needed, contact Karnak Technical Services at 1-800-526-4236.

When installed properly, this product will help reduce energy costs. Actual savings will vary based on geographical location and individual building characteristics. Consult your product manufacturer, roofing contractor, or call 1-888-STAR-YES (1-888-782-7937) for more information.

Please see page 212 for additional mold and safety information.







